

Application No.: 09/980,910

Docket No.: NY-DNAG 224-US

IN THE ABSTRACT

Replace the abstract with the following new abstract:

Metallic surfaces are coated with an aqueous, acidic phosphate solution containing 10 to 60 g/l zinc, 0.5 to 40 g/l manganese, 50 to 300 g/l phosphate ions calculated as  $P_2O_5$ , and optionally other components.